

NextDent Try-In

Specifications

Property	Requirement	Result	ISO standard
Flexural modulus	≥ 1500 MPa	1882	ISO 20795-1
Biocompatibility	Non-cytotoxic	Comply	ISO 10993-1
Biocompatibility	Non-mutagenic	Comply	ISO 10993-1
Biocompatibility	Not a sensitizer	Comply	ISO 10993-1

The material is available in 1 Kg containers.